

SI73

PP

Hanwha TotalEnergies Petrochemical co. Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	23	g/10min	ASTM D 1238
Temperature	230	°C	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	37.8	MPa	ASTM D 638
Elongation at Break	60	%	ASTM D 638
Flexural Modulus	2403	MPa	ASTM D 790
Rockwell Hardness	R 105	-	ASTM D 785
Izod Impact notched, 1/8 in	49.1	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
DTUL @ 66 psi	138	°C	ASTM D 648
Other properties			
Density	1100	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Features

High Crystallinity, Low Odor, Thermal Stability

Chemical Resistance

General Chemical Resistance

Certifications

Food contact

Applications

Electrical and Electronical, Packaging

Regional Availability

Asia Pacific