

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	0.7	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	33	MPa	ISO 527
Yield strain	8	%	ISO 527
Flexural modulus, 23°C	1300	MPa	ISO 178
Izod notched impact strength, +23°C	2	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	60	°C	ISO 75-1/-2
Vicat softening temperature, A	155	°C	ISO 306

## Characteristics

### Processing

Pipe/Tube Extrusion, Sheet Extrusion

### Special Characteristics

Heat stabilized or stable to heat

### Features

Thermal Stability, Homopolymer

### Certifications

Food contact

### Regional Availability

Europe, Asia Pacific