

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	8	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	34	MPa	ASTM D 638
Elongation at Yield	8	%	ASTM D 638
Flexural Modulus	1300	MPa	ASTM D 790
Thermal properties			
ASTM Data			
DTUL @ 66 psi	107	°C	ASTM D 648
Vicat Temperature	152	°C	ASTM D 1525

Characteristics

Processing

Film Extrusion

Regional Availability

Europe, Asia Pacific

Additives

Antiblocking agent