

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|-------|---------|---------------|
| ISO Data | | | |
| Melt flow index, MFI | 0.3 | g/10min | ISO 1133 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |

| Mechanical properties | Value | Unit | Test Standard |
|-------------------------------------|-------|-------------------|---------------|
| ISO Data | | | |
| Yield stress | 26 | MPa | ISO 527 |
| Yield strain | 16 | % | ISO 527 |
| Stress at break | 22 | MPa | ISO 527 |
| Flexural modulus, 23°C | 830 | MPa | ISO 178 |
| Izod notched impact strength, +23°C | 432 | kJ/m ² | ISO 180/1A |

| Thermal properties | Value | Unit | Test Standard |
|--|-------|------|---------------|
| ISO Data | | | |
| Temp. of deflection under load, 0.45 MPa | 88 | °C | ISO 75-1/-2 |
| Vicat softening temperature, A | 145 | °C | ISO 306 |

Characteristics

Processing

Injection Molding, Pipe/Tube Extrusion, Sheet Extrusion

Special Characteristics

Heat stabilized or stable to heat

Features

Copolymer, Random Copolymer

Regional Availability

Europe, Asia Pacific