

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	1.8	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	24	MPa	ISO 527
Yield strain	12	%	ISO 527
Flexural modulus, 23°C	900	MPa	ISO 178
Izod notched impact strength, +23°C	14	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	1.5	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-20	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	50	°C	ISO 75-1/-2
Vicat softening temperature, A	135	°C	ISO 306

## Characteristics

### Processing

Blow Molding

### Special Characteristics

Sterilizable

### Features

Copolymer, Random Copolymer

### Applications

Medical

### Regional Availability

Europe, Asia Pacific