

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.8	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	24	MPa	ISO 527
Yield strain	12	%	ISO 527
Flexural modulus, 23°C	900	MPa	ISO 178
Izod notched impact strength, +23°C	20	kJ/m ²	ISO 180/1A
Izod notched impact strength	1.5	kJ/m ²	ISO 180/1A
Temperature	-20	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	50	°C	ISO 75-1/-2
Vicat softening temperature, A	135	°C	ISO 306

Characteristics

Processing

Blow Molding

Special Characteristics

Transparent

Features

Copolymer, Random Copolymer

Certifications

Food contact

Applications

General Purpose

Regional Availability

Europe, Asia Pacific