Starpylen MH0200A

PP — Eurostar Engineering Plastics

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	**4500**	MPa	ISO 527
Stress at break	**18**	MPa	ISO 527
Strain at break	**25**	%	ISO 527
Flexural modulus, 23°C	**3000**	MPa	ISO 178
Izod impact strength, +23°C	**20**	kJ/m²	ISO 180/1U
Izod notched impact strength, +23°C	**3**	kJ/m²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	**64**	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	**1910**	kg/m³	ISO 1183

Characteristics

Processing
Injection Molding, Other Extrusion

Features
Low Odor

Delivery form
Pellets

Regional Availability
Europe

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.