

Starpnylen MH0255A

PP

Eurostar Engineering Plastics

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	14	MPa	ISO 527
Strain at break	5	%	ISO 527
Flexural modulus, 23°C	4400	MPa	ISO 178
Izod impact strength, +23°C	8	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	2	kJ/m ²	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	2550	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding, Other Extrusion

Features

Low Odor

Delivery form

Pellets

Regional Availability

Europe