

**T300**

PP

SINOPEC Shanghai Gaoqiao Company

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Melt flow index, MFI	3	g/10min	

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Yield stress	31	MPa	
Flexural modulus, 23°C	1300	MPa	

S: These properties are reported by the producer according standards that are different to our defaults.

**Characteristics****Processing**

Sheet Extrusion

**Regional Availability**

Asia Pacific

**Certifications**

Food contact, Food approval FDA 21 CFR