

TAIRIPRO® K9010

PP

Formosa Chemicals & Fibre Corp.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	9	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.016	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	21.6	MPa	ASTM D 638
Elongation at Break	200	%	ASTM D 638
Flexural Modulus	981	MPa	ASTM D 790
Rockwell Hardness	R 78	-	ASTM D 785
Izod Impact notched, 1/8 in	490	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	83.4	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 66 psi	110	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Injection pressure	3 - 6	MPa	-

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified

Features

Copolymer, Impact Copolymer

Certifications

Food contact, Food approval FDA 21 CFR, RoHS compliant

Regional Availability

Asia Pacific