

TASNEE PP H4120

PP

Tasnee

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	33	MPa	ISO 527
Yield strain	10	%	ISO 527
Rockwell hardness	R 100	-	ISO 2039-2
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	163	°C	ISO 11357-1/-3
Temp. of deflection under load, 0.45 MPa	102	°C	ISO 75-1/-2
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Applications

Packaging

Delivery form

Pellets, White

Regional Availability

Near East/Africa

Features

Low Odor, Homopolymer