

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	55	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	1400	MPa	ISO 527
Yield stress	23	MPa	ISO 527
Yield strain	4	%	ISO 527
Flexural modulus, 23°C	1400	MPa	ISO 178
Izod notched impact strength, +23°C	7	kJ/m ²	ISO 180/1A
Izod notched impact strength	4	kJ/m ²	ISO 180/1A
Temperature	-20	°C	-
Rockwell hardness	R 80	-	ISO 2039-2
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	92	°C	ISO 75-1/-2
Processing Recommendation Injection Molding			
Melt temperature	190 - 250	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Additives

Release agent

Special Characteristics

Anti-static, High impact or impact modified

Features

Blending Resin, Low Odor, Nucleated, Copolymer, Impact Copolymer

Certifications

Food contact, Food approval BfR, Food approval 1935/2004/EC, Food approval 10/2011, Food approval FDA 21 CFR

Applications

Automotive, Packaging, Toys

Regional Availability

Europe