

Product Texts

Flammability @3.2mm nom. HB
thickn.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Charpy impact strength, +23°C	40	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	12	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	148	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	159	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	137	°C	ISO 306

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1130	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Regional Availability**

North America, South and Central America