

TECNOPRENE® HK6

PP

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at break	90	MPa	ISO 527
^[C] Strain at break	3.3	%	ISO 527
^[C] Charpy notched impact strength, +23°C	10.8	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	150	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1130	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Regional Availability**

North America, Europe, Asia Pacific, South and Central America,
Near East/Africa