

Product Texts

Color: green
100% PCR

Processing/Physical Characteristics

ISO Data

	Value	Unit	Test Standard
Melt flow index, MFI	4	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Other properties

	Value	Unit	Test Standard
Density	918	kg/m ³	ISO 1183

Characteristics

Processing

Film Extrusion

Delivery form

Pellets

Features

Homopolymer

Certifications

Recycled Resin Content

Regional Availability

Europe