

Product Texts

Color: grey
100% PCR

Processing/Physical Characteristics

| | Value | Unit | Test Standard |
|----------------------|--------------|-------------|----------------------|
| ISO Data | | | |
| Melt flow index, MFI | 15 | g/10min | ISO 1133 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |

Mechanical properties

| | Value | Unit | Test Standard |
|------------------|--------------|-------------|----------------------|
| ISO Data | | | |
| Tensile Modulus | 800 | MPa | ISO 527 |
| Tensile Strength | 22 | MPa | ISO 527 |

Other properties

| | Value | Unit | Test Standard |
|------------------|--------------|-------------------|----------------------|
| Density | 900 | kg/m ³ | ISO 1183 |
| Moisture Content | 0.03 | % | - |

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Features

Copolymer

Certifications

Recycled Resin Content

Regional Availability

Europe