

Product Texts

Color: white
100% PCR

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	18	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Charpy notched impact strength, +23°C	3.5	kJ/m ²	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	905	kg/m ³	ISO 1183
Moisture Content	0.04	%	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets, White

Features

Copolymer

Certifications

Recycled Resin Content

Regional Availability

Europe