

Product Texts

Color: mixed f. grey
100% PIR

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	30	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1350	MPa	ISO 527
Tensile Strength	30.1	MPa	ISO 527
Strain at break	30.1	%	ISO 527

Other properties

	Value	Unit	Test Standard
Density	910	kg/m ³	ISO 1183
Moisture Content	0.05	%	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Features

Homopolymer

Certifications

Recycled Resin Content

Regional Availability

Europe