

**Product Texts**

Color: white  
 Regranulat, PPC, ca. 30 % SIS  
 100% PIR

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	32	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	438	MPa	ISO 527
Tensile Strength	12.8	MPa	ISO 527
Strain at break	405	%	ISO 527

Other properties	Value	Unit	Test Standard
Density	904	kg/m <sup>3</sup>	ISO 1183
Moisture Content	0.05	%	-

**Characteristics****Processing**

Injection Molding

**Features**

Copolymer

**Delivery form**

Pellets, White

**Certifications**

Recycled Resin Content

**Special Characteristics**

High impact or impact modified

**Regional Availability**

Europe