

**THERMOFIL® FR H050B00**

PP

Sumika Polymer Compounds UK Ltd.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>1000</b>	MPa	ISO 527
Tensile Strength	<b>23</b>	MPa	ISO 527
Charpy notched impact strength, +23°C	<b>14</b>	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Burning behav. at 1.5 mm nom. thickn.	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>1.6</b>	mm	-
Burning behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>3.0</b>	mm	-

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>950</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Special Characteristics**

Flame retardant

**Regional Availability**

North America, Europe, Asia Pacific

**Features**

Copolymer