

**Thermylene® P-9900-1761**

PP

Asahi Kasei

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	5	g/10min	ISO 1133

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	28	MPa	ISO 527
Flexural modulus, 23°C	1300	MPa	ISO 178
Flexural strength	38	MPa	ISO 178
Charpy notched impact strength, +23°C	10	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	53	°C	ISO 75-1/-2

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	910	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Special Characteristics**  
High impact or impact modified**Regional Availability**  
North America