

TI6800WV

PP

Braskem

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	80	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Izod Impact notched, 1/8 in	120	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	60	J/m	ASTM D 256
Temperature	-20	°C	-

Characteristics**Processing**

Injection Molding

Features

Nucleated, Copolymer

Additives

Release agent

Regional Availability

North America, Europe

Special Characteristics

High impact or impact modified