

TITANPRO® SM398

PP

Lotte Chemical Titan (M) Sdn. Bhd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	10.5	g/10min	ASTM D 1238
Temperature	230	°C	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	26.5	MPa	ASTM D 638
Elongation at Yield	14	%	ASTM D 638
Flexural Modulus	1030	MPa	ASTM D 790
Rockwell Hardness	R 80	-	ASTM D 785
Izod Impact notched, 1/8 in	58.7	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	80	°C	ASTM D 648
Other properties			
ASTM Data			
Water Absorption, 24hr	0.02	%	ASTM D 570
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Special Characteristics

Transparent

Features

Non Blooming, Copolymer, Random Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

Asia Pacific