

TOTAL 4030 S05

PP

TotalEnergies

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	3.3	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	1450	MPa	ISO 527
Yield stress	33	MPa	ISO 527
Yield strain	10	%	ISO 527
Flexural modulus, 23°C	1350	MPa	ISO 178
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	5	kJ/m ²	ISO 180/1A
Rockwell hardness	R 90	-	ISO 2039-2
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	162	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	100	°C	ISO 75-1/-2
Vicat softening temperature, A	150	°C	ISO 306
Vicat softening temperature, B	85	°C	ISO 306
Other properties			
Density	905	kg/m ³	ISO 1183
Bulk density	525	kg/m ³	-

Characteristics**Processing**

Film Extrusion

Regional Availability

Europe

Features

Homopolymer