

**TOTAL 4663**

PP

TotalEnergies

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	3.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	1300	MPa	ISO 527
Yield stress	25	MPa	ISO 527
Yield strain	7	%	ISO 527
Flexural modulus, 23°C	1200	MPa	ISO 178
Charpy notched impact strength, +23°C	20	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	18	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	5.5	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-20	°C	-
Rockwell hardness	R 82	-	ISO 2039-2
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	50	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	92	°C	ISO 75-1/-2
Vicat softening temperature, A	147	°C	ISO 306
Vicat softening temperature, B	70	°C	ISO 306
<b>Other properties</b>			
Density	905	kg/m <sup>3</sup>	ISO 1183
Bulk density	525	kg/m <sup>3</sup>	-

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

High impact or impact modified, U.V. stabilized or stable to weather

**Features**

Copolymer

**Regional Availability**

Europe