

**TOTAL 6298**

PP

TotalEnergies

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	9	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Flexural modulus, 23°C	850	MPa	ISO 178
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	140	°C	ISO 11357-1/-3
Vicat softening temperature, A	125	°C	ISO 306
<b>Other properties</b>			
<b>ISO Data</b>			
Density	902	kg/m <sup>3</sup>	ISO 1183
Bulk density	525	kg/m <sup>3</sup>	-

**Characteristics****Processing**

Film Extrusion

**Certifications**

Food contact

**Additives**

Antiblocking agent

**Applications**

Packaging

**Features**

Weldable, Copolymer, Random Copolymer

**Regional Availability**

Europe