

TOTAL 10641

PP

TotalEnergies

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	44	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1600	MPa	ISO 527
Yield stress	27	MPa	ISO 527
Yield strain	4	%	ISO 527
Flexural modulus, 23°C	1500	MPa	ISO 178
Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	7.5	kJ/m ²	ISO 180/1A
Izod notched impact strength	4	kJ/m ²	ISO 180/1A
Temperature	-20	°C	-
Rockwell hardness	R 100	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	57	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	114	°C	ISO 75-1/-2
Vicat softening temperature, A	148	°C	ISO 306
Vicat softening temperature, B	80	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	905	kg/m ³	ISO 1183
Bulk density	525	kg/m ³	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Anti-static

Features

Nucleated, Copolymer

Certifications

Food contact

Applications

Packaging

Regional Availability

Europe