

TOTAL rPPC35GR

PP

TotalEnergies

Product Texts

Circular Compound rPPC35GR is a high MFR polypropylene of dark grey color with good impact/stiffness balance, containing at least 50% of post-consumer recycled (PCR) originating from post-consumer household waste collected in Western European countries.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	35	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Flexural modulus, 23°C	1400	MPa	ISO 178
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	1000	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Certifications

Recycled Resin Content

Features

Copolymer

Regional Availability

Europe