

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	1400	MPa	ISO 527
Yield stress	33	MPa	ISO 527
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	140	°C	ISO 11357-1/-3
Temp. of deflection under load, 0.45 MPa	92	°C	ISO 75-1/-2
Vicat softening temperature, A	124	°C	ISO 306

Characteristics

Processing

Rotational Molding

Delivery form

Pellets, Powder, Natural Color

Special Characteristics

Transparent

Features

High Gloss, Low Warpage, Copolymer, Random Copolymer

Regional Availability

Europe