

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	800	MPa	ISO 527
Yield stress	20	MPa	ISO 527
Flexural modulus, 23°C	850	MPa	ISO 178
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	140	°C	ISO 11357-1/-3
Temp. of deflection under load, 0.45 MPa	64	°C	ISO 75-1/-2
Vicat softening temperature, A	114	°C	ISO 306

Characteristics

Processing

Rotational Molding

Delivery form

Pellets, Powder, Black, Natural Color

Special Characteristics

High impact or impact modified

Features

High Gloss, Low Warpage, Copolymer, Random Copolymer

Regional Availability

Europe