

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	800	MPa	ISO 527
Yield stress	20	MPa	ISO 527
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	138	°C	ISO 11357-1/-3
Temp. of deflection under load, 0.45 MPa	71	°C	ISO 75-1/-2
Vicat softening temperature, A	114	°C	ISO 306

### Characteristics

#### Processing

Rotational Molding

#### Delivery form

Pellets, Powder, Natural Color

#### Special Characteristics

High impact or impact modified

#### Features

High Gloss, Low Warpage, Copolymer, Random Copolymer

#### Regional Availability

Europe