

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	32	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	29	MPa	ASTM D 638
Elongation at Yield	11	%	ASTM D 638
Rockwell Hardness	R 85	-	ASTM D 785
Izod Impact notched, 1/8 in	100	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	105	°C	ASTM D 648
Melting Temperature	163	°C	ASTM D 3418
Vicat Temperature	148	°C	ASTM D 1525
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding

#### Delivery form

Pellets

#### Special Characteristics

High impact or impact modified

#### Features

Low Odor, Low Warpage, Copolymer, Impact Copolymer

#### Certifications

Food contact, Food approval FDA 21 CFR

#### Applications

Automotive

#### Regional Availability

Asia Pacific