

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3.8	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	34	MPa	ASTM D 638
Elongation at Yield	13	%	ASTM D 638
Rockwell Hardness	R 100	-	ASTM D 785
Izod Impact notched, 1/8 in	40	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	104	°C	ASTM D 648
Melting Temperature	163	°C	ASTM D 3418
Vicat Temperature	152	°C	ASTM D 1525
Other properties			
Density	903	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets

Certifications

Food contact, Food approval FDA 21 CFR

Features

Low Odor, Homopolymer

Regional Availability

Asia Pacific