

Volaprint PP Transparent

PP

Volaprint 3 de-store

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1100	MPa	ISO 527
Yield stress	29	MPa	ISO 527
Yield strain	13	%	ISO 527
Charpy notched impact strength, +23°C	26	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, B	72	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ISO 1183

Characteristics

Processing

Additive Manufacturing

Delivery form

Monofilament

Special Characteristics

Transparent

Certifications

Food contact

Regional Availability

Europe