

WG350C

PP

Borealis A/S

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	18	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, A	142	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	90	°C	-
Pre-drying - Time	4	h	-
Zone 1	200	°C	-
Zone 2	240	°C	-
Zone 3	280	°C	-
Nozzle temperature	280	°C	-

Characteristics**Processing**

Coating

Certifications

Food contact

Special Characteristics

Sterilizable

Applications

Packaging

Features

Heat Sealable

Regional Availability

Europe