

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.6	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Strength	30	MPa	ISO 527
Strain at break	15	%	ISO 527
Flexural modulus, 23°C	1800	MPa	ISO 178
Flexural strength	35	MPa	ISO 178
Izod impact strength, +23°C	N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	40	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	60	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	120	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Electrical properties			
ASTM Data			
Surface Resistivity	1000	Ohm	ASTM D 257
Other properties			
Water absorption	0.04	%	Sim. to ISO 62
Humidity absorption	0.01	%	Sim. to ISO 62
Density	1010	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.05	%	-
Melt temperature	200 - 260	°C	-
Mold temperature	40 - 80	°C	-
Back pressure	0 - 1	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

Europe

Special Characteristics

Increased electrical conductivity, High impact or impact modified