

**X 30 S**

PP

Petrochemical Commercial Co.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	9	g/10min	ISO 1133
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Flexural modulus, 23°C	1500	MPa	ISO 178
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	115	°C	ISO 75-1/-2
Vicat softening temperature, A	155	°C	ISO 306
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Applications**

Packaging

**Regional Availability**

Europe, Asia Pacific, Near East/Africa