

Y1600

PP

SINOPEC Shanghai Gaoqiao Company

Processing/Physical Characteristics	Value	Unit	Test Standard
Other Standards^[S]			
Melt flow index, MFI	16	g/10min	

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
Other Standards^[S]			
Yield stress	31.4	MPa	
Flexural modulus, 23°C	1300	MPa	

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Regional Availability

Asia Pacific