

YUHWA POLYPRO 5014

PP

Korea Petrochemical Ind. Co., Ltd

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3.2	g/10min	ASTM D 1238
Mold Shrinkage, MD	0.015	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	35.3	MPa	ASTM D 638
Elongation at Break	500	%	ASTM D 638
Flexural Modulus	1472	MPa	ASTM D 790
Rockwell Hardness	R 96	-	ASTM D 785
Izod Impact notched, 1/8 in	39	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	162	°C	ASTM D 3418
Vicat Temperature	152	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Features**

Homopolymer

Certifications

Food contact, Food approval FDA 21 CFR

Applications

General Purpose, Packaging

Regional Availability

Asia Pacific