

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	22	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	164	°C	ISO 11357-1/-3
Vicat softening temperature, A	117	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	904	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Regional Availability

Europe