

YUHWHA POLYPRO SB9302

PP

Korea Petrochemical Ind. Co., Ltd

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2	g/10min	ASTM D 1238
Mold Shrinkage, MD	0.016	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	25.5	MPa	ASTM D 638
Elongation at Break	500	%	ASTM D 638
Flexural Modulus	1177	MPa	ASTM D 790
Rockwell Hardness	R 83	-	ASTM D 785
Izod Impact notched, 1/8 in	589	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	59	J/m	ASTM D 256
Temperature	-20	°C	-

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	165	°C	ASTM D 3418
Vicat Temperature	152	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	910	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified

Features

Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

Asia Pacific