

YUNGSOX 1120D

PP

Formosa Plastics Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Molding shrinkage, parallel	1.5	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	44.1	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	1570	MPa	ISO 178
Rockwell hardness	R111	-	ISO 2039-2

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Heat stabilized or stable to heat

Features

Homopolymer

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Electrical and Electronical, General Purpose

Regional Availability

Asia Pacific