

Z 30 S

PP

Petrochemical Commercial Co.

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------------|----------------------|
| ISO Data | | | |
| Melt flow index, MFI | 2.5 | g/10min | ISO 1133 |
| Mechanical properties | | | |
| ISO Data | | | |
| Flexural modulus, 23°C | 1550 | MPa | ISO 178 |
| Thermal properties | | | |
| ISO Data | | | |
| Temp. of deflection under load, 0.45 MPa | 118 | °C | ISO 75-1/-2 |
| Vicat softening temperature, A | 155 | °C | ISO 306 |
| Other properties | | | |
| Density | 900 | kg/m ³ | ISO 1183 |

Characteristics**Processing**

Other Extrusion

Regional Availability

Europe, Asia Pacific, Near East/Africa