

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.5	g/10min	ISO 1133
Temperature	200	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
ASTM Data			
Melt Flow Index, MFI	1.5	g/10min	ASTM D 1238
Temperature	200	°C	-
Load	5	kg	-
Mold Shrinkage, MD	0.0045	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Tensile Modulus	3300	MPa	ISO 527
Stress at break	55	MPa	ISO 527
Flexural strength	95	MPa	ISO 178
ASTM Data			
Tensile Modulus	3300	MPa	ASTM D 638
Tensile Strength at Break	58	MPa	ASTM D 638
Flexural Strength	95	MPa	ASTM D 790
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	95	°C	ISO 75-1/-2
Vicat softening temperature, A	107	°C	ISO 306
ASTM Data			
DTUL @ 264 psi	95	°C	ASTM D 648
Vicat Temperature	107	°C	ASTM D 1525
Other properties			
Density	1050	kg/m ³	ISO 1183
Density	1050	kg/m ³	ASTM D 792
Processing Recommendation Extrusion			
Melt temperature	210 - 240	°C	-

Characteristics

Processing

Other Extrusion

Special Characteristics

Heat stabilized or stable to heat

Features

Foamable

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

Applications

General Purpose, Packaging

Regional Availability

South and Central America