

# 3M™ Dyneon™ PTFE Paste TF 2029Z

PTFE

Dyneon

Other properties	Value	Unit	Test Standard
Density	2150	kg/m <sup>3</sup>	ISO 1183
Bulk density	450	kg/m <sup>3</sup>	-

Film Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Stress at break, parallel	34	MPa	ISO 527-3
Maximum strain, parallel	380	%	ISO 527-3

## Characteristics

### Processing

Other Extrusion

### Delivery form

Powder

### Applications

Electrical and Electronical

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa