

3M™ Dyneon™ PTFE Paste TF 2072Z

PTFE

Dyneon

Other properties	Value	Unit	Test Standard
Density	2170	kg/m ³	ISO 1183
Bulk density	470	kg/m ³	-

Film Properties	Value	Unit	Test Standard
ISO Data			
Stress at break, parallel	35	MPa	ISO 527-3
Maximum strain, parallel	470	%	ISO 527-3

Characteristics

Processing

Wire/Cable Extrusion

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa