

INOFLON™ GN7300

PTFE

Gujarat Fluorochemicals Limited

Mechanical properties	Value	Unit	Test Standard
Other Standards^[S]			
Tensile Strength	33	MPa	ASTM D 4895
Elongation at Break	350	%	ASTM D 4895

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Bulk Density	450	kg/m ³	-
Other Standards^[S]			
Density	2180	kg/m ³	ASTM D 4895

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics**Processing**

Pipe/Tube Extrusion, Wire/Cable Extrusion

Delivery form

Powder, White

Special Characteristics

Transparent

Features

Tribologic Grade, Weldable

Chemical Resistance

General Chemical Resistance, Environmental Stress Crack Resistance, Solvent Resistance

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific