

INOFLON™ M695

PTFE

Gujarat Fluorochemicals Limited

Processing/Physical Characteristics	Value	Unit	Test Standard
Other Standards^[5]			
Mold Shrinkage, MD	0.05	mm/mm	ASTM D 4894

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
Other Standards^[5]			
Tensile Strength	30	MPa	ASTM D 4894

S: These properties are reported by the producer according standards that are different to our defaults.

Thermal properties	Value	Unit	Test Standard
Other Standards^[5]			
Melting Temperature	334	°C	ASTM D 4894

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Bulk Density	300	kg/m ³	-
Other Standards^[5]			
Density	2160	kg/m ³	ASTM D 4894

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics**Processing**

Film Extrusion, Sheet Extrusion

Features

Fatigue Resistance, Weldable

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Transparent