

LUBEFLON® K 301 FDA

PTFE

Polis S.r.l.

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------------|----------------------|
| ISO Data | | | |
| Melt flow index, MFI | 0.05 | g/10min | ISO 1133 |
| Temperature | 380 | °C | - |
| Load | 21 | kg | - |
| Thermal properties | | | |
| ISO Data | | | |
| Melting temperature, 10°C/min | 335 | °C | ISO 11357-1/-3 |
| Other properties | | | |
| Density | 2160 | kg/m ³ | ISO 1183 |
| Bulk density | 450 | kg/m ³ | - |

Characteristics**Delivery form**

Powder, White

Features

Low Odor, Tribologic Grade

Certifications

Food contact, Food approval 1935/2004/EC, Food approval FDA 21 CFR

Regional Availability

Europe