

LUBEFLON® KP 650 FDA

PTFE

Polis S.r.l.

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	330	°C	ISO 11357-1/-3
Other properties			
Density	2160	kg/m ³	ISO 1183
Bulk density	450	kg/m ³	-

Characteristics**Delivery form**

Powder, White

Features

Blending Resin, Low Odor, Tribologic Grade

Certifications

Food contact, Food approval 1935/2004/EC, Food approval FDA 21 CFR

Regional Availability

Europe